



DESCRIPTION	TOA Primer Surfacer Grey Spray #56 is based on high quality nitrocellulose, modified alkyd resin and special pigments that recommend to use as all-purposes primer. The properties of this primer are flexible, fast dry and good adhesion on plastic, metal, wood and etc.															
TYPICAL USE	Recommend to apply TOA Primer Surfacer Grey Spray #56 as a primer before topcoat with TOA All-Purposes Spray (or other topcoat sprays) to enhance the adhesion.															
PHYSICAL PROPERTIES	<p>Type : Acrylic Lacquer Resin</p> <p>Color : Grey</p> <p>Gloss : Matt</p> <p>Pressure : 4 Bar</p> <p>Flash Point : -10 °C</p> <p>Coverage(by theory) : 1.40 sq.meter / coat / can</p> <p>Remark – Actual surface coverage is depend on application condition, experience, technique, shape and dimension of the object that need to spray on.</p> <table border="0"> <tr> <td rowspan="2">Drying Time</td> <td>Temperature</td> <td>25°C</td> <td>30°C</td> </tr> <tr> <td>Surface dry</td> <td>15 – 20 minutes</td> <td>10 – 15 minutes</td> </tr> <tr> <td></td> <td>Hard dry</td> <td>60 – 70 minutes</td> <td>45 – 60 minutes</td> </tr> <tr> <td rowspan="2">Recoatible Time</td> <td>Minimum</td> <td>15 –20 minutes</td> <td>8 – 10 minutes</td> </tr> </table>	Drying Time	Temperature	25°C	30°C	Surface dry	15 – 20 minutes	10 – 15 minutes		Hard dry	60 – 70 minutes	45 – 60 minutes	Recoatible Time	Minimum	15 –20 minutes	8 – 10 minutes
Drying Time	Temperature		25°C	30°C												
	Surface dry	15 – 20 minutes	10 – 15 minutes													
	Hard dry	60 – 70 minutes	45 – 60 minutes													
Recoatible Time	Minimum	15 –20 minutes	8 – 10 minutes													
	APPLICATION INFORMATION	<p>Surface Preparation : The surface must be clean and free of dirt, grease, oil, wax, salt, old paint and other contaminants. : Chalky surfaces or loose material must be removed by stiff brush. : The surface must be clean with suitable cleansing solution and water then rinse thoroughly with fresh water and allow to fully dry.</p> <p>Primer 1. Before use, shake the can of TOA Primer Surfacer Grey Spray #56 thoughly around 2 minutes and shake periodically during spray. 2. Spray with distance from the required object around 20 – 25 cm and spray from left to right and top to bottom of the object.(Depend on skill and experience) 3. The first coat must be thin and allow to dry at least 15 minutes before spray the second coat.</p> <p>Topcoat : Apply TOA All-Purposes Spray (or other topcoat sprays) at least 2 coats.</p> <p>Application Method : Spray</p> <p>Condition During Application : Use respiratory mask with charcoal and dust filter. For prolonged or repeated handling, use nitrile gloves or polyvinyl alcohol gloves. Use safety eye wear designed to protect against splash of liquids. : No smoking.</p>														
STORAGE	<p>: The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.</p> <p>: After used, the container must be kept tightly closed.</p>															
SHELF LIFE	: 36 months at 25 – 30°C (from manufacturing date)															
PACKAGE	: 400 cc / Can															



HEALTH AND SAFETY

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. In case of eye contact, immediately flush the eye with plenty of water at least 15 minutes and get medical attention.

: For more informations on health, safety, hazards and precautions for use of this product, please ask for Material Safety Data Sheet.

DISCLAIMER

: The informations in this Technical Data Sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

คุณลักษณะ	สเปร์ยรองพื้นเทา ทีโอเอ เบอร์ 56 ผลิตจากโพลีเอสเตอร์เรซิน โมดิไฟด์ อัลลิจด์ เรซิน และผงสีชนิดพิเศษ เป็นสีรองพื้นเอนกประสงค์สำหรับงานทั่วไป มีคุณสมบัติแห้งไว มีความยืดหยุ่น และสามารถยึดเกาะได้ดีบน พลาสติก โลหะ ไม้ และวัสดุอื่นๆ																
การใช้งาน	ใช้เป็นสีรองพื้นก่อนพ่นทับหน้าด้วย สีสเปร์ยเอนกประสงค์ ทีโอเอ (หรือสีสเปร์ยแบบอื่นที่ต้องการ) เพื่อเพิ่มการยึดเกาะกับพื้นผิว																
ข้อมูลทางเทคนิค	<p>ประเภทของสี โพลีเอสเตอร์เรซิน และ โมดิไฟด์ อัลลิจด์ เรซิน</p> <p>สี เทา</p> <p>ระดับความเงา แบบด้าน</p> <p>ความดัน 4 บาร์</p> <p>จุดควบไฟ -10 °C</p> <p>การปกคลุมพื้นผิว (โดยทฤษฎี) 1.40 ตารางเมตร ต่อ เทียว ต่อ กระป๋อง</p> <p>หมายเหตุ : ค่าการปกคลุมพื้นผิวขึ้นกับสภาวะระหว่างใช้งาน ประสบการณ์ เทคนิคการพ่น รวมถึงรูปร่างและขนาดกว้าง-ยาว ของวัตถุที่นำมาพ่น</p> <table><tr><td>ระยะเวลาแห้ง</td><td>อุณหภูมิ</td><td>25°C</td><td>30°C</td></tr><tr><td></td><td>แห้งผิว</td><td>15 – 20 นาที</td><td>10 – 15 นาที</td></tr><tr><td></td><td>แห้งแข็ง</td><td>60 – 70 นาที</td><td>45 – 60 นาที</td></tr><tr><td>ระยะเวลาแห้งก่อนพ่นทับ</td><td>อย่างน้อย</td><td>10 – 15 นาที</td><td>8 – 10 นาที</td></tr></table>	ระยะเวลาแห้ง	อุณหภูมิ	25°C	30°C		แห้งผิว	15 – 20 นาที	10 – 15 นาที		แห้งแข็ง	60 – 70 นาที	45 – 60 นาที	ระยะเวลาแห้งก่อนพ่นทับ	อย่างน้อย	10 – 15 นาที	8 – 10 นาที
ระยะเวลาแห้ง	อุณหภูมิ	25°C	30°C														
	แห้งผิว	15 – 20 นาที	10 – 15 นาที														
	แห้งแข็ง	60 – 70 นาที	45 – 60 นาที														
ระยะเวลาแห้งก่อนพ่นทับ	อย่างน้อย	10 – 15 นาที	8 – 10 นาที														
ระบบการใช้งาน	<p>การเตรียมพื้นผิว : พื้นผิวที่จะใช้งานต้องสะอาด ปราศจากฝุ่น, คราบไขมัน, คราบสี, คราบเกลือ, สีเก่า และสิ่งปนเปื้อนต่างๆ : พื้นผิวที่เป็นขอสลัค หรือ เสื่อมสภาพ ต้องขัดทำความสะอาดด้วยแปรงไนลอน : ทำความสะอาดพื้นผิวด้วยน้ำและน้ำยาทำความสะอาดที่เหมาะสม แล้วล้างด้วยน้ำสะอาดอีกครั้ง ก่อนทาสีให้แห้งสนิท</p> <p>การรองพื้น 1. ก่อนใช้งานควรเขย่ากระป๋อง สเปร์ยรองพื้นเทา ทีโอเอ เบอร์ 56 ประมาณ 2 นาที จนเสียงลูกแก้วดังสม่ำเสมอ และเขย่าเป็นระยะระหว่างพ่น 2. พ่นห่างจากชิ้นงานประมาณ 20 – 25 เซนติเมตร โดยพ่นจากซ้ายไปขวา และ จากบนลงล่าง (ขึ้นกับความหนืดและประสบการณ์) 3. เทียวแรกควรพ่นบางๆ แล้วทิ้งให้แห้งอย่างน้อย 15 นาที ก่อนพ่นทับที่เทียวที่ 2</p> <p>การพ่นสีทับหน้า วิธีใช้งาน : พ่นทับหน้าด้วยสีสเปร์ยเอนกประสงค์ ทีโอเอ (หรือสีสเปร์ยแบบอื่นที่ต้องการ) อย่างน้อย 2 เทียว</p> <p>ข้อแนะนำเวลาปฏิบัติงาน : การพ่น : ควรสวมอุปกรณ์ป้องกันภัยส่วนบุคคล เช่น แว่นตา ถุงมือ และ ฝาปิดจมูก : ห้ามสูบบุหรี่ระหว่างการใช้งาน</p>																
การเก็บรักษา	<p>: สินค้าจำเป็นต้องเก็บรักษาตามข้อกำหนด ควรเก็บในที่แห้ง มีอากาศถ่ายเทดี ไม่ควรเก็บในบริเวณที่รับแสงแดดโดยตรง ต้องเก็บให้พ้นจากแหล่งกำเนิดความร้อนและประกายไฟ</p> <p>: หลังใช้งาน ควรปิดฝาให้สนิท</p>																
อายุผลิตภัณฑ์	: 36 เดือน ที่อุณหภูมิ 25 – 30°C (นับจากวันที่ผลิต)																
ขนาดบรรจุ	: 400 ซีซี ต่อ กระป๋อง																

ข้อมูลสุขภาพและความปลอดภัย

: กรุณาดูข้อควรระวังที่ติดไว้หน้ากระป๋อง การทำงานสีควรทำในที่ที่อากาศถ่ายเทสะดวก
อย่าสูดหายใจละอองของสี ควรใส่หน้ากากเมื่อทำการพ่นสีและพยายามเลี่ยงมิให้สัมผัสผิวหนัง
ถ้าสีหกใส่ผิวหนังควรล้างด้วยน้ำสะอาดกับสบู่ทันที ถ้าถูกตาควรล้างด้วยน้ำสะอาดทันทีและ
รีบไปพบแพทย์

: รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในข้อมูลด้านความปลอดภัย

การสงวนสิทธิ์เรียกร้อง

: รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในข้อมูลด้านความปลอดภัย
: รายละเอียดข้างบนนี้ได้มาโดยการทดลอง และจากประสบการณ์ที่ผ่านมา เนื่องจากสีถูกนำไปใช้
ในภาวะที่แตกต่างกันเราจึงไม่สามารถรับประกันในสิ่งอื่นใดนอกจากคุณภาพของสีเท่านั้น
บริษัทของสงวนสิทธิ์ที่จะเปลี่ยนแปลงข้อมูลโดยมิต้องแจ้งล่วงหน้า